



Issuance Date 10/06/15
Revision Date 18/02/20
Revision No. 20-01

Technical Data Sheet

AS-5000 Aqua Nails



Physical Properties

Base:

Synthetic rubber

Appearance:

Thick paste

Colours:

Brown

Curing time:

24 – 72 hours

Tack-free Time:

<5 minutes
(at 25 °C & 50% R.H)

Application temperature:

-20 °C – 38 °C

Service temperature:

-30 °C – 60 °C

Storage:

Store in a dry and cool place
with temperature below
30 °C.

Shelf Life:

12 months

Packaging:

Content	Quantity / carton
300 mL cartridge	24



Scan and learn

Visit product page:

<https://www.alsealmarketing.com/as-5000-aqua-nails/>

Description

ALSEAL Aqua Nails is a one-component, high performance, paste-like construction adhesive sealant formulated to bond a variety of common construction materials. It has strong initial grab, superior adhesion and will not slump on vertical surfaces.

Features

- ♦ Mirror and polystyrene safe
- ♦ Superior adhesion on most substrates
- ♦ Strong initial grab
- ♦ Non-drip paste

Applications

- ♦ Ideal for bonding most construction materials: wood, particle board, metal, concrete, fibre-reinforced cement board, ceramics, bricks, flooring panels.
- ♦ Can be used on polystyrene and mirror.

Technical Data

Curing system	: Solvent evaporation
Density	: 1.16 g/mL
Solid content	: 77 %
Lap shear strength (ASTM D1002)	: 3.2 N/mm ² (Wood-to-wood)
Freeze/Thaw stability	: 5 cycles

Usage Instructions

1. Surfaces must be clean, dry and free of dirt, grease, oil or water.
2. For a neat finish, apply masking tape and remove it before construction adhesive skins over.
3. Cut tip off and puncture the internal foil seal with nozzle. Cut nozzle at 45° angle to desired bead-width and apply to substrate with cartridge gun.
4. **Two-way contact** (Lighter substrate bonding): Apply adhesive onto substrate to be bonded, press firmly, and pull apart. Allow to tack-off for 10 to 30 seconds and press firmly together again. Contact areas should be tapped with a rubber mallet to ensure intimate contact.
5. **One-way method** (Heavier substrate bonding): Apply adhesive onto substrate to be bonded, press firmly, and securely fasten them together (clamp, nail, screw, etc.). Retain fastening for a minimum of 24 hours.
6. Any wet or partially wet adhesive can be removed with a piece of cloth. Dried adhesive is best removed with scraper or by sanding.

Clean Up

- ♦ Wet sealants can be cleaned up with acetone or mineral spirits.
- ♦ Cured sealants can only be removed mechanically.

Alseal Marketing Sdn Bhd

www.alsealmarketing.com



AS-5000 Aqua Nails

Coverage

A 300 mL cartridge will cover 10 meters of 6 mm bead.

Limitation

Not recommended for outdoor use.

Caution

Highly flammable liquid and vapour. Causes skin irritation. May cause an allergic skin reaction. May cause drowsiness or dizziness. Suspected of damaging fertility or the unborn child. May cause damage to the nervous system through prolonged or repeated exposure by inhalation. Harmful to aquatic life with long lasting effects. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Do not breathe fumes. Use only outdoors or in a well-ventilated area. Wear protective gloves and eye protection. IF exposed or concerned: Get medical advice/attention. Store locked up. Keep out of reach of children. Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

Disclaimer

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.